



Adsorption Of Lead (II) Utilizing Avocado Pear Seed (American Persea) In Waters Contaminated in Huanta Ayacucho

Tulio Celestino Paytan Montañez^{1*}, Juan Quispe Rodríguez², Isaac Aliaga Barrera³,

^{1*,2,3}Institución de Afiliación. Ciudad, País, Universidad Nacional Autónoma de Huanta, Ayacucho, Perú.

¹Email: tpaytan@unah.edu.pe. Orcid 0000-0001-9199-2241. ²Email: jquispe@unah.edu.pe.

Orcid 0000-0003-1767-686X. ³Email: inaliaga@unah.edu.pe. Orcid 0000-0002-1478-1886.

***Corresponding Author:** Tulio Celestino Paytan Montañez

*Institución de Afiliación. Ciudad, País, Universidad Nacional Autónoma de Huanta, Ayacucho, Perú.

Email: tpaytan@unah.edu.pe.

Orcid 0000-0001-9199-2241.

Article History	Abstract
Received: 02 June 2023 Revised: 23 Sept 2023 Accepted: 30 Nov 2023	<i>The avocado pear seed like residue has the capability of adsorption for the metals weighed with the methodology of isothermal of adsorption, Pseudo secondly order, and Freundlich respectively and results demonstrate than (II) equal Pb's capability of adsorption to 74,375 mg g gets an initial concentration of 494,45 mg L, pH of 4,5 and size of particle of 125 m and the size of particle influences significantly the capability of adsorption, and obtained him a bigger capability of adsorption to a size of particle of 125 m and the minor the capability of adsorptionM and the pH's interaction and the initial concentration act significantly on the capability of adsorption of the contaminant to a size of particle of 425. The bigger capability of adsorption got an initial concentration of 494 itself. 45 mg L and size of particle of 125 m, capability of adsorption decreases initial concentration of 48,79 mg L and a size of particle of 425 the m (II) fitted up Pb's data of the isothermal in the process of adsorption better to Langmuir's mathematical model, with R²=0.9904's value, which indicates a biosorption in mono-cape with a maximum capacity of sortion of 72,9927 mg g. You came to an end, that the avocado pear seed (American Persea) presents an efficient possibility of adsorption of the ions Pb (II) caning to be employed for the use to decontaminate the water in nature.</i>
CC License CC-BY-NC-SA 4.0	Keywords: Adsorption, kinetics of adsorption, isothermal of adsorption, avocado pear seed

Introduction

The adsorption enables minimizing the generation of toxic waste matter and the recuperation of metal (1) the treatment of residual waters that incorporate the removal of metallic ions cause comes from multiple worldwide investigations (2), the biomass act as an ionic natural inter-moneychanger that attracts the solution's metals (3) the experiments of adsorption came true to different concentrations, they utilized models of isothermal of adsorption and his mathematical formulation to describe the equilibriums of adsorption, his use to eliminate metals weighed of watery means (4), being the objective of the investigation to evaluate is feasible herCapability of adsorption of lead (II) utilizing avocado pear seed (*American Persea*) in contaminated waters, whose importance is friendly to the ambient midway stops various treatment of contaminated waters, grounds and gases, in the same way specially for the removal of metals weighed, at present methods like the ionic interchange, the inverse osmosis and the precipitation utilize themselves, but these processes are costly in his operation and maintenance, which have proven that this process allows decreasing the quantities of contaminants in the effluents, since it is a precise, highly effective and cost-reducing method. The experiments of adsorption came true for lots as from solutions of metallic salts to different concentrations, they utilized

models of isothermal of adsorption and his mathematical formulation to describe the equilibriums of adsorption. The maximum capacities of adsorption obtained experimentally came from 18.6 mgg (II) 1 for the copper ions and - 1 for the cadmium ions of 22.7 mgg - (II). Both isothermal they correspond to one isothermal of type H, indicating a loud affinity of adsorption and a loud adsorbent interaction adsorbato, his use to eliminate metals weighed of watery means is feasible (4). They utilized the models of isothermal of Langmuir and Freundlich to describe the mechanism of adsorption in the model of isothermal Pb²⁺'s adsorption describes + in the natural zeolita in clay and better of Langmuir. (KR) they calculated the factors of separation as from the isothermal one belonging to Langmuir (5). The time of optimal contact to stir the bigger percentage of lead, aluminum and cadmium comes from 7,83g, 7,75g and 8,83g and 90 min's time (2). The initial concentrations and endings of cadmium and lead of the residual waters after the process of leak I eat: PH determined itself by means of potenciometría (6). The influence of several factors was investigated, including the initial concentration of ions, the pH, the time of contact and the dose of adsorbent, in Pb²⁺'s adsorption + to identify the optimal conditions of adsorption. The experimental data fit to well pseudo's kinetic model secondly order (R² 0.9997) and to the equation of isothermal of Freundlich (R² 0.9950), besides, the bigger adsorption caught up with pH itself 5.5. The maximum calculated capacity, q_m, determined g went from 50 mg as from Langmuir's model (7). The experiments of cultivation of grounds suggested that Pb's effective contents at the processed grounds materializes of alum bettered with hot alkali he was (p 0.05) the treatises significantly younger with the other ones three types of plasma of alum (8). They take 500 their mL and to him 1g of hydrothermal basic pulverized product is added on. At a later time, they took rates of 5mL in intervals of 20, 40, 60, 80, 100, 120, 180, 240 and 300 minutes (9). Pb²⁺'s experiments of adsorption + in equilibrium and kinetics, where the breakeven data fit to Dubinin Radushkevich's model (R² $\approx \leq 0.990$) with capability of maximum adsorption of 12.16 mg better g with. In like manner, for the data of kinetics, the model with better adjustment was the one belonging to Elovich (R² $\approx \leq 0.994$). However, the kinetics of adsorption also fitted to Pseudo Primer's models order (R² $\approx \leq 0.990$) and Pseudo Segundo order (R² $\approx \leq 0.992$), with moral values of adsorption of 10.54 mg g and 15.59 mg g respectively (10). Findings: (II) equal Pb's bigger capability of adsorption to 74,375 mg g gets an initial concentration of 494,45 mg L, pH of 4,5 and size of particle of 125 m and you determined the presence of functional groups like hidroxilo, carbonilo, aminos through FTIR's technique and carboxylic acids and results proved that the capability of sortion is directly proportional to the quantity of ions of metal and the interaction of the pH and the initial concentration they act significantly on the capability of adsorption of the contaminant. The bigger capability of adsorption got an initial concentration of 494 itself. 45 mg L and size of particle of 125 m, and the capability of adsorption decreases of 48,79 mg L and a size of particle of 425 to initial concentration m.

MATERIALS And MÉTODOS

The materailes that were utilized were Crucibles, Cápsulas Petri, Baguetas, Glasses of once 200, 250 and 100 were precipitated m, Fiolas 1000, 500, 250, 100 and 50 ml, Probeta 50, 25, 10 and 5 mL, Pipetas 5 and 10 mL, Juego of sifters, Mortero, Matraces Erlenmeyer 500 and 100ml, Embudos, Luna of clock, Desecador, Papel slow filter, magnetic Agitador, Termómetro and reagents: Distilled water, Plomo's Nitrato (Merck, p.a.), Sodium hydroxide NaOH (Merck, p.a.), Nitric acid (Merck, p.a.) And the methodology to evaluate the influence of the independent variables on the clerk, the experimental design of type **Factorial** used 42, data itself they will be obtained by work of field directly of the team of proofs and defendants with methods of descriptive statistics.

1 shows the chosen factors itself in the board, and the following sizes of particle (425 m, 300 m, 250 m and 125 m) and initial Pb's concentrations were considered (II) (48,79 ppm, 195,76 ppm, 346,29 ppm and 494,45 ppm).

RESULTS

Huanta's province is one of the first producers of avocado pear. You prepared the biomass utilized in this study as from the avocado pear seeds that you find in abundance at Huanta's province, these were recollected naturally in July of the 2022 one belonging to Huanta's Market, you extracted the nutshell that covers the seed with avocado pear and it was proceeded to accomplishing the cleanliness and washing to eliminate the particles of dirtiness, they got cut in little pieces to make easy the time of drying and at a later time they were dehydrated to the ambient midway during five days to the temperature of the environment of 23 C on the average at Huanta's city.

BOARD 1. Initial concentrations of PB's solutions (II)


Pb(NO ₃) ₂ (g)	mg/L (nominal)	mg/L (experimental)
0.0800	50	48.79
0.3201	200	195.76
0.5602	350	346.29
0.8002	500	494.45

SOURCE: THE AUTHOR'S OWN ELABORATION.

The obtained results suggested that the isothermal one belonging to Freundlich is the best-suited model to describe Plomo's adsorption, characterizing like a chemical adsorption, with a capability of adsorption of 27,5867 mg g, correlation coefficient of r^2 0,9954 and the intensity of adsorption or favorabilidad's grade of 5,0968. The value of n 1 represents that adsorption is in favorable conditions (11). Corroborating these findings, Castillo et to the., (2017) they mention than the best description of the process of adsorption of the ions Pb (II) R^2 observed in Freundlich's model based in the regression coefficients 0,964 himself. The model of Freundlich, with a value of bigger n than 1, you indicate a great affinity between the adsorbent existing and the adsorbato, which classifies like a chemical adsorption, as to the value K_f , indicates the capability of adsorption of the adsorbent, that is, as much as the principal be, the capability of adsorption of the present Pb in the solution will be more favorable (13).

The results of Langmuir's model for Pb's adsorption (II) you assume uniform energy for the sortion in a very cape, determined him 71,942 mg's capability of maximum adsorption g, Constante of equilibrium of sortion of 0,1574 L mg and a correlation coefficient 0,9863, moral values than probably, they lift the adsorbent's surface you enlarged the places of adsorption (14.15).

Pb's process of adsorption (II) in show was evaluated to the time of contact to determine the time of equilibrium between the solution and the metallic ion.




Represent 02: Dynamics of adsorption of lead (ii)

Achieving 23,727 mg's capability of adsorption g in the first 20 minutes, next it remained approximately constant with a q_e of approximately of 24,015 to the 240 minutes, the time of equilibrium of the process achieved approximately the 50 minutes that they mention that the maximum rate of elimination was produced in 45 minutes for the Pb, and 60 minutes for the CD, and it was established on top of these times that the system had attained the break-even point. The fast rate of initial adsorption can relate with the loud availability of active places of the surface of the bioadsorbente (bananas nutshell) for the adsorption of the ions lead (16.17).

Characterization of the Biomass


Infrared spectroscopy with transformed of Fourier (FTIR). The study of the superficial chemistry and determination of the functional groups of adsorbent material, the homogeneous signs were placed 4000 on cm^{-1} 's spectral range – 400 cm^{-1} . Specters FTIR the obtained graficando were the signs of transmittance versus number of wave. The specter FTIR of the adsorbent (avocado pear seed) identified the different kinds of vibratory correspondent frequencies to the different functional present groups on the surface of the biomass, as shown in the figure 03. $3273,95 \text{ cm}^{-1}$'s wavelength 1 the N belongs to the vibrations of stretching and flexion H and to the

functional groups of alcohol - OH that also you find yourself in this range (18). Regarding 2918,82 and 2849,06 cm's peaks 1 correspond to the symmetric and asymmetric stretching of the groups C Or – H and CH₂ present in fatty acids, and 1736, 39 cm's peak 1 is related to the groups carbonilos C -. 1374,21 cm's band 1 to 1312,64 cm 1 corresponds to vibrations of stretching of – CH (14)



The specter *represents* 03 flir of the biosorbente before the process of adsorption.


The bioadsorbente's specter I present 3240 cm's wideband ¹ that is attributed (NH), as well as 2920 cm ¹ to aminas attributed to alcanos's presence (C H), to 2927,7, and as well as a peak 1620 cm ¹ due to the vibration of tension and flexion in the diagram, respectively attributed to aminas's presence (Or H). Also they located to the tensile vibrations the following attributed band: 990 cm ¹, respectively, attributed to the presence of carboxylic acids (Or H).



Represent 04. Isothermal adjustment of the data calculated to the different.


Source: The author's own elaboration.

The adjustments came true following first Pseudo's models order, Pseudo secondly order, Elovich and diffusion intraparticular, using the data of the study of time of contact.



Represent 04. I study kinetic to be an of adsorption of lead a Co 494,45 mg L of Pb (II) and Co 195,76 mg Pb's L (II) with size of particle of 125 m.

Of 48,79 ppm's solution extracted him 4 times 50 mL and 0,05, 0,10, 0,18 and 0,40 grams of the originating biomass of the avocado pear seed (*American Persea*), these were weighed Erlenmeyer to be once 800 rpm were stirred, initial pH placed in 4 flask themselves respectively (4,5) and for 2 hours.



Represent 05. Influence of Pb's dose of the biosorbente in the percentage of removal (II).

Pb's increment of the percentage of removal of ions as you go increasing the biosorbente's dose can be observed. Getting 85,43 %'s percentage of removal with 0.18 g's dose.

Discussion OF THE RESULTS

Likewise, you show up than the correlation coefficients (r^2) of Elovich's kinetic models and Difusión Intraparticular comes from 0,9565 and 0,9585, adminiculating that the process of adsorption had a chemical reaction and a penetration of the adsorbato toward the adsorbent respectively, and the order did not have herself in account granted that you lacked of a linearity in relation to the first model Pseudo. Corroborating these results, Mahmood et to the., (2019) they mention that the kinetic model that better you fit up in Pb's process of adsorption (II) is Pseudo's equation secondly order, utilizing Pino's sawdust like adsorbent to a pH of 4,5. The kinetic study utilizing avocado pear seeds (natural form) like adsorbent for Pb's removal (II) of a contaminated solution correlated to Pseudo's model second order better, in a process of reactors for lots, achieving the equilibrium in 60 minutes of contact and 23,85 mg's capability of adsorption g (19).

You demonstrate the determination of dosaje's curve, having different leaden concentrations (30 ppm to 130 ppm) and varying the quantity of residual biomass generated of *American Persea's* seed (0.05 g to 0,5 g), achieving a percentage of removal of 62 to 97 %. Better results utilizing 0,15 gr of biomass, with the one that surpasses the 80 % of adsorption itself were obtained. CITATION The percentage of adsorption increases and you confirm with the graphic repetitions, assuming that the percentage of elected adsorption must be determined in the range of the curve formed during the development of the process, postulate than the optimal mass to utilize this within the range of 80 to 90 % of adsorption. Analysis of the superficial chemistry of the (avocado pear seeds) intervening biosorbente Infrared Espectroscopia with Transformada of Fourier (FTIR). This technique helped to know the superficial chemistry of the adsorbent material before the process of biosorption (avocado pear seeds),. The technique FTIR allowed identifying functional groups that find themselves present on the surface of the avocado pear seeds, which allowed performing an important role in the removal of organic and inorganic contaminants.

CONFLICT OF INTEREST.

The authors thank Huanta's National Autonomous University through the funds the academic support and financier FOCAM for, however, conflict of academic interest in the development of research work, where all authors and coauthors authorized the scientific article's publication does not exist.

FINDINGS

(II) equal Pb's bigger capability of adsorption to 74,375 mg g gets an initial concentration of 494,45 mg L, pH of 4,5 and size of particle of 125 m.

Through FTIR's technique determined him the presence of functional groups like hidroxilo, carbonilo, aminos and carboxylic acids which would be favoring the process of biosorption and the size of particle has influence significantly in the capability of adsorption, and obtained him a bigger capability of adsorption to a size of particle of 125 m and the minor the capability of adsorption to a size of particle of 425 m.

The bigger capability of adsorption turned out well utilizing (II) equal Pb's initial concentration to 494,45 mg L, the results proved that the capability of sorption is directly proportional to the quantity of ions of metal and the pH's interaction and the initial concentration act significantly on the capability of adsorption of the contaminant. The bigger capability of adsorption got an initial concentration of 494 itself. 45 mg L and size of particle of 125 m, and the capability of adsorption decreases of 48,79 mg L and a size of particle of 425 to initial concentration m.

(II) you fitted up Pb's data of the isothermal in the process of adsorption better to the mathematical model of Langmuir, with $R^2=0.9904$'s value, which indicates a biosorption in mono-cape with a maximum capacity of sorption of 72,9927 mg g and with respect, Second Orden with R^2 's value adjusted to the data of the best treatment Pseudo's kinetic model better 0,9474, what I indicate than the adsorbato himself quimisorbe on the biosorbente's surface.

CONFLICT OF INTEREST

On the basis of the experience acquired in the development of work and visualizing his complementation, new investigations will be able to be suggested, when it be the case,, or some practical implications derived of research work and the future fact-finding lines.

Bibliographic REFERENCES

- Barrier RH, Horruitiner TB, Lamela OC. Adsorption of chrome (I SAW) and lead (II) on dry biomass of *Kluyveromyces marxianus* CCEBI 2011. Internet reviews Cuban. 2022;34(1):111–30. Available from: http://scielo.sld.cu/pdf/ind/v34n1/2224-5421_ind_34-01-111.pdf
- Rosemary bonilla H, Salud D, Oro And, Carlos J, Vera L. Comparación of kinetic isothermic models during the adsorption of intervening lead *Azolla caroliniana*. Technical University of Crush It, Authorize of Chemical Sciences. 2022;99–114.
- Morales Fonseca D, Ruiz Tovar K, Martínez Salgado MM, Soto Guzmán AB, Falcony Guajardo C, Rodríguez Vázquez R, et al. I unroll of a laminar bioadsorbente with *Phanerochaete hyper-tolerant* chrysosporium to cadmium, to nickel and to the lead for the treatment of waters. Re-v Iberoam Micol. 2010 Jul;27(3):111–8.
- Ramón De The Santos C, Barajas Fernández J, Pérez Hernández G, Hernández Rivera MÁ, Díaz Flores LL. Adsorption of copper (II) and cadmium (II) in aqueous suspensions of biogenic nanostructured CaCO_3 . The Society's Bulletin Espanola of Ceramics and Glass. 2019 Jan 1;58(1):2–13.
- Rakhym AB, Seilkhanova GA, Kurmanbayeva TS. Adsorption of lead (II) ions from water closet solutions natural with zeolite and chamotte clay. Mater Today Pro-C. 2020; 31:482–5.
- Sanchez JIM. Faculty of chemical sciences and of health race of medical sciences. Repositorio Technical University of Crush It. 2020;1–31.
- Alghamdi EA, to the Odayni AB, Saeed WS, to the Kahtani To, Alharthi FA, Aouak T. Efficient adsorption of lead (II) from aqueous phase solutions using polypyrrole based activated coal. Materials. 2019 Jun 1;12(12).
- Li N, Fu Q, Guo B, Liu C, Li H, Ding Y. Adsorption of Pb^{2+} by ameliorated alum materializes in water closet and soil. PLoS One. 2019 Jan 1;14(1).
- Omar J, García P, Sánchez AEC, Dismissing P, Jiménez Q, Álvarez OC. Adsorption OF IONS (II) INTERVENING Pb A Solid. Coat Center Sugar. 2022;107–14.
- Gonzaga To, Rimaycuna J, Cruz GJF, Herrera THE, Gómez MM, Solis JL, et al. Removal of present lead in watery solutions utilizing biocarbón produced on the basis of coronta of corn. Mangrove Internet. 2021;18(1):35–43. Available from:
- Yogeshwaran V, Priya AK. Removal of hexavalent chromium concentration from the aqueous solution using chemically treated sugarcane bagasse powder. Journal Indian Chemical Society. 2020;97(9):1467–77.
- Castle FC, Dunoyer AT, Vasquez Y. Capacidad of adsorption of lead with inter-moneychangers catiónicos of coal xantado. And coat UDCA Actualidad Divulgación Científica. 2017;20(2):425–33.
- Menezes JMC, Silva Bento gives AM, gives Silva JH, of Paula Filho FJ, Costa gives JGM, Coutinho HDM, et al. Equilibrium, kinetics and thermodynamics of lead (II) adsorption in bioadsorbent composed by *Caryocar coriaceum* Wittm barks. Chemosphere. 2020;261(1):1–7.
- Tiled C, Herrera AP, Nuñez JR. Competitive adsorption of Neither (II) and Pb (II) on residual materials lignocelulósicos. Andean investigations. 2015;17(31):1355–67.
- Mendoza LV, Molina NF. Cd's, Pb's and Zn's BIOSORCIÓN FOR PRE-PROCESSED BIOMASS OF RED ALGAE, CÁSCARA OF ORANGE And PRICKLY PEAR. Science and Engineering Neo-Of Granada. 2014;25(1):43–60.
- Koksharov SA, Aleeva SV, Lepilova OV. Description of adsorption interactions of lead ions with functional groups of pectin containing substances. J Mole Liq. 2019;283(1):606–16.
- Mahmood Q, Asif M, Shaheen S, Hayat MT, Ali S. Cadmium Contamination in Water and Soil. In: Cadmium Toxicity and Tolerance in Plants. 1st ed. Pakistan: Elsevier; 2019. p. 141–61.
- Chand P, Shil AK, Sharma M, Pakade YB. Improved adsorption of cadmium ions from aqueous solution using chemically modified apple pomace: Mechanism, kinetics, and thermodynamics. Int Biodeterior Biodegradation. 2014; 90:8–16.
- Sun Kou M of the R, Obregón Valence D, Pinedo Flowers Á, Ann Lucy Walls Doig, Aylas Dried Peach J. Adsorption Of Heavy Metals Using Activated Carbons Prepared as from Seeds Of Sea Current. Coat of the Chemical Society of the Peru. 2014;80(4):225–36.